


O.C.-FORM® 150 UL AS

O.C.-FORM 150® UL AS is a polyurethane soft foam impregnated with modified acrylates and laminated on both sides with an aluminium film reinforced with glass fabric.

Characteristics of O.C.-FORM® 150 UL AS

- material basis: O.C.-FORM® 150 UL ALU
- sealing with large tolerance compensation characteristics and closed lateral surface
- specifically for the sealing of joints and gaps
- density of 150 kg/m³
- high mechanical strength due to aluminium coating



Fire protection according to DIN EN 45545 Part 2: 2016-02 R1-HL3

Test report number: 11300/39365

<u>Applications</u>	sealing of joints and gaps, where the soft and elastic sealing needs to be provided with a closed lateral coating
<u>Tightness</u>	air permeability 1,25m ³ /h per running meter of joint (Internal pressure 150 Pa., thickness 30 mm, compression by. 20%)
<u>Compressive stress</u>	3,45 kPa (compression by. 20%)
<u>Dimensions</u>	material thickness of 8 mm and higher
<u>Forms of delivery</u>	tapes with self-adhesive
<u>Storage stability</u>	unlimited, with self-adhesive (SK) 12 months (at temperatures of +5 °C to +35 °C, keep dry and free of dust, no direct exposure to sunlight or other heat sources)
<u>Resistance</u>	gainst UV, weather conditions and ageing and against all liquids used in the engine compartment
<u>Environment</u>	free of heavy metal (Pb, Hg, Cd, Cr VI), prohibited substances as mentioned in GADSL- and RoHS-list and brominated flame retardant (PBB, PBDE, penta- and octabromine derivatives)